

Release K100 H

Description

RELEASE K 100 H is a high molecular weight synthetic polymer in powder form. When in solution, it is a very efficient release agent for tapes with an excellent resistance to heat and humidity.

Its particular chemical structure guarantees a perfect anchorage to polyolefin film. RELEASE K 100 H is produced by a particular polymerization technique without heavy metal catalysts. The product is completely silicone free.

Application

RELEASE K 100 H can be used on corona treated as well as on untreated films. Concentration ranges from 0.5% to 3% solids, depending upon film type, coating equipment and desired release effect. RELEASE K 100 H is soluble in aromatic and aliphatic solvents, like: hexane/IPA: toluene.

Technical Specifications

Method of analysis	MU	Standard
1. Total Solids	%	99±1
5. Melting Range	°C	94 - 104

Handling

Slowly add RELEASE K 100 H to solvents under continuous stirring, at a temperature between 40 and 50°C. Extra care while handling flammable solvents is advisable.

Packaging

The product is supplied in fibre drums (20 kg).

Storing

RELEASE K 100 H can be stored safely at almost all normal temperatures below its melting point. When in solution, it must be stored at temperatures not below 20-25°C to prevent gelification. In case of partial or total solidification, stir well and heat up to 40-50 °C. The product will return completely fluid. Do not coat if the solution is not completely clear or if solid particles can be seen. The solution must be handled with care due to the presence of solvent (avoid inhalation, skin contact and flame presence).

Use within 24 months from production date (unopened and in the original packaging).

Notes

RELEASE K 100 H may be used as a release agent in adhesive sealing tape for indirect food-contact applications.

Ref. Opinion Letter of 22/02/2016 "FDA Status of Release K100 H for Adhesive Tapes Applications", Keller & Heckman LLP.